

FILMOFLEX MESH C 270 Bs1d0



Features

- 270g/m² PVC flexface, coated
- 100% high tenacity polyester yarn with PVC coating on both sides
- without PVC liner on the back, especially for XXL-printer
- improved print quality by extra thread in the grid
- matt surface
- flame retardancy

Areas of Application

- designed for medium-term indoor and outdoor applications
- ideal for large format banners, scaffolding banners, construction fences etc.
- for hot or high frequency welding pre-testing is necessary
- does not contain any substances of concern, according to current SVHC candidate list / REACH compliant
- suitable for (eco) solvent inks, UV-curable inks and latex inks of the 1st and 2nd generation. Third generation latex inks are conditionally suitable

Processing & Handling

- to avoid problems in processing ensure adequate drying before finishing (drying time of min.48 hours is recommended)
- do not dry in rolled condition
- expected outdoor durability up to 18 months for Central-Europe climate (storm damages and other environmental influences excepted)
- for larger projects we recommend using only material from the same production batch
- due to the production process, it is possible that pressure marks occur on the last 3-4 meters of the material. This is due to a combination of material properties and the core winding and cannot be completely avoided
- a seam at least 5cm wide is necessary when using eyelets. The eyelets should have a maximum spacing of 40cm.
- ALWAYS store the rolls together with the original label / batch number
- no claims or complaints will be accepted without the batch or production number

FILMOFLEX MESH C 270 Bs1d0

≈ FILMOflex

TECHNICAL DATA

Material	polyester fabric with PVC-coating
Weight	approx. 270 g/m ² (+ 5%), without liner
Weaving construction	12 x 12 inch DIN 60001
Weight of fabric	approx. 115 g/m ² (+ 5%)
Weight of PVC coating	approx. 155 g/m ² (+ 5%)
Thread strength	~ 1000 x 1000 Denier
Tensile strength	Warp: 1200 N/5cm Weft: 1100 N/5cm DIN53354 method 6A
Tearing strength	Warp: 300 N Weft: 280 N DIN53356 method 7A
Suitable temperature	-15 +70 °C
Air permeability	2649 mm/s
Fire protection class	B-s1,d0 - EN 13501-1 B1 - DIN 4102-1
Storage conditions	18°C - 25°C, 40 - 60% relative humidity
Shelf life	6 months in original packaging

Le informazioni pubblicate riguardanti i nostri prodotti sono basate su conoscenze ed esperienze pratiche. Gli acquirenti devono indipendentemente determinare, prima dell'uso, l'idoneità del materiale per l'utilizzo che ne vogliono fare. L'acquirente deve assumersi tutti i rischi per qualsiasi uso, funzionamento e applicazione del materiale. Noi siamo responsabili del

danno solo per il prezzo d'acquisto con esclusione di danni diretti o accidentali. Tutte le informazioni fornite servono solo a descrivere il prodotto e non riguardano assicurazioni in senso giuridico. Le specifiche sono soggette a modifiche senza preavviso, salvo errori ed omissioni.