

Filmoflex Blockout Matt 610

ITEM	DATA	UNIT	TEST METHOD
Fabric	High tenacity yarns 100% PES (500D)		DIN EN ISO2060
Construction	Weaving 28*28	inch	DIN60001
Total weight	610	g/sq.m	DIN53352 BS3424 method5A
Weight of fabric	120	g/sq.m	DIN53352 BS3424 method5B
Weight of PVC coating	490	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp: 1850 Weft: 1350	N/5cm	DIN53354 BS3424 method6A
Tearing strength	Warp: 235 Weft: 220	N	DIN53356 BS3424 method7A
Adhesion	80	N/5cm	DIN53357 BS3425 method9B
Suitable temperature	-20 ----- +70	°C	DIN53372 BS3424 method10
Flame retardancy		FR B1	
Lacquering		No	

The indexes above are on average, so there will be $\pm 5\%$ tolerance for actual material.