

Filmoprint PP Grey Back

Introduction

- **Base substrate:** PP in 170 micron
- Coated grey back, very opaque
- **Coated:** Acrylic 25 micron on printing side, 15 micron grey on back
- **Ink absorption:** Solvent, ECO solvent, UV, Latex
- **Durability:** Up to 2 year

Advantages

- Economical and environmental friendly Roll up solution

Features

PROPERTIES	UNIT	TEST METHOD	RESULT
Substrate	Mic	DIN60001	170
Substrate density			0.7
Finished weight	Gram/mq	DIN EN ISO 2286-2	155
Finished Thickness	Mic		210 ± 5
Tensile strength at MD	N/5cm	DIN53354	
Tensile strength at CD	N/5cm	DIN53354	
Coating Thickness	Mic		20
Coating peeling strength	N/5cm	GB/T1040	No peeling
Whiteness			92
Glossiness			86/8
Glue thickness	Mic		
Liner	Mic		
Peel Strength for glue	N/5cm	GB/T2913	
Min Storage Temperature	°C / °F		-70 / -94
Temperature range	°C	DIN53372	-70 ~ +80

Le informazioni pubblicate riguardanti i nostri prodotti sono basate su conoscenze ed esperienze pratiche. Gli acquirenti devono indipendentemente determinare, prima dell'uso, l'idoneità del materiale per l'utilizzo che ne vogliono fare. L'acquirente deve assumersi tutti i rischi per qualsiasi uso, funzionamento e applicazione del materiale. Noi siamo responsabili del danno solo per il prezzo d'acquisto con esclusione di danni diretti o accidentali. Tutte le informazioni fornite servono solo a descrivere il prodotto e non riguardano assicurazioni in senso giuridico. Le specifiche sono soggette a modifiche senza preavviso, salvo errori ed omissioni.