

## Filmoflex Blockout Matt 440

ITEM	DATA	UNIT	TEST METHOD
<b>Fabric</b>	High tenacity yarns 100%PES(250D*250D)		DIN EN ISO2060
<b>Construction</b>	Weaving 36*36	inch	DIN60001
<b>Total weight</b>	440	g/sq.m	DIN53352 BS3424 method5A
<b>Weight of fabric</b>	78	g/sq.m	DIN53352 BS3424 method5B
<b>Weight of pvc coating</b>	362	g/sq.m	DIN53352 BS3424 method5B
<b>Tensile strength</b>	Warp: 1300	N/5cm	DIN53354 BS3424 method6A
	Weft: 1030		
<b>Tearing strength</b>	Warp: 115	N	DIN53356 BS3424 method 7A
	Weft: 105		
<b>Adhesion</b>	80	N/5cm	DIN53357 BS3425 method9B
<b>Suitable temperature</b>	-20 -----+70	°C	DIN 53372 BS3424 method10
<b>Flame retardancy</b>		B1	
<b>Lacquering</b>		No	

The indexes above are on average, so there will be  $\pm 5\%$  tolerance for actual material.